



Development of Thermal Barriers for Solid Rocket Motor Nozzle Joints

Bruce M. Steinetz
Glenn Research Center, Cleveland, Ohio

Patrick H. Dunlap, Jr.
Modern Technologies Corporation, Middleburg Heights, Ohio

The NASA STI Program Office . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the Lead Center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized data bases, organizing and publishing research results . . . even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to help@sti.nasa.gov
- Fax your question to the NASA Access Help Desk at (301) 621-0134
- Telephone the NASA Access Help Desk at (301) 621-0390
- Write to:
NASA Access Help Desk
NASA Center for Aerospace Information
7121 Standard Drive
Hanover, MD 21076



Development of Thermal Barriers for Solid Rocket Motor Nozzle Joints

Bruce M. Steinetz
Glenn Research Center, Cleveland, Ohio

Patrick H. Dunlap, Jr.
Modern Technologies Corporation, Middleburg Heights, Ohio

Prepared for the
35th Joint Propulsion Conference and Exhibit
cosponsored by the AIAA, ASME, SAE, and ASEE
Los Angeles, California, June 20-24, 1999

National Aeronautics and
Space Administration

Glenn Research Center

Acknowledgments

The authors greatly acknowledge Doug Frost's and Steve Hicken's (Thiokol) thermal barrier test results; Bruce Bond's (Albany-Techniweave) assistance in fabricating the thermal barriers; and Tom Doeberling's and Lauren Yee's (NASA) assistance in test support.

Trade names or manufacturers' names are used in this report for identification only. This usage does not constitute an official endorsement, either expressed or implied, by the National Aeronautics and Space Administration.

Available from

NASA Center for Aerospace Information
7121 Standard Drive
Hanover, MD 21076
Price Code: A03

National Technical Information Service
5285 Port Royal Road
Springfield, VA 22100
Price Code: A03

DEVELOPMENT OF THERMAL BARRIERS FOR SOLID ROCKET MOTOR NOZZLE JOINTS

Bruce M. Steinetz*

National Aeronautics and Space Administration
Glenn Research Center
Cleveland, Ohio 44135

Patrick H. Dunlap, Jr.†

Modern Technologies Corporation
Middleburg Heights, Ohio 44130

Abstract

The Space Shuttle solid rocket motor case assembly joints are sealed using conventional O-ring seals. The 5500+°F combustion gases are kept a safe distance away from the seals by thick layers of insulation. Special joint-fill compounds are used to fill the joints in the insulation to prevent a direct flowpath to the seals. On a number of occasions, NASA has observed in several of the rocket nozzle assembly joints hot gas penetration through defects in the joint-fill compound. The current nozzle-to-case joint design incorporates primary, secondary and wiper (innermost) O-rings and polysulfide joint-fill compound. In the current design, 1 out of 7 motors experience hot gas to the wiper O-ring. Though the condition does not threaten motor safety, evidence of hot gas to the wiper O-ring results in extensive reviews before resuming flight. NASA and solid rocket motor manufacturer Thiokol are working to improve the nozzle-to-case joint design by implementing a more reliable J-leg design and a thermal barrier.

This paper presents burn-resistance, temperature drop, flow, and resiliency test results for several types of NASA braided carbon-fiber thermal barriers. Burn tests were performed to determine the time to burn through each of the thermal barriers when exposed to the flame of an oxyacetylene torch (5500 °F), representative of the 5500 °F solid rocket motor combustion temperatures. Thermal barriers braided out of carbon fibers endured the flame for over 6 min, three times longer than the solid rocket motor burn time. Tests were performed on two thermal barrier braid architectures, denoted Carbon-3 and Carbon-6, to measure the temperature drop across and along the barrier in a compressed state when subjected to the flame of an oxyacetylene torch. Carbon-3 and Carbon-6 thermal barriers were excellent insulators causing temperature drops through their diameter from 2500 to 2800 °F. Gas temperatures 1/4" downstream of the thermal barrier were within the downstream Viton O-ring temperature limit of

600 °F. Carbon-6 performed extremely well in subscale rocket "char" motor tests when subjected to hot gas at 3200 °F for an 11-sec. rocket firing, simulating the maximum downstream joint cavity fill time. The thermal barrier reduced the incoming hot gas temperature by 2200 °F in an intentionally oversized gap defect, spread the incoming jet flow, and blocked hot slag, thereby offering protection to the downstream O-rings.

Introduction

The need for high temperature (1500 to 2000 °F) compliant seals in advanced gas turbine engine designs led to the development of rope seals braided out of newly developed ceramic fibers and superalloy wires. Previous seal research yielded several braided rope seal designs that demonstrated the ability to both seal and serve as compliant mounts under aggressive temperature and pressure requirements.^{1,2} However, Steinetz and Dunlap³ showed that these seals do not last for more than a few seconds when subjected to the extremely hot 5500+ °F combustion gases that are found in the Space Shuttle Solid rocket motor. Thus, other materials were considered to evolve the braided rope seal design into a thermal barrier for use at extreme transient temperatures.

The Space Shuttle reusable solid rocket motor (RSRM) assembly joints are sealed using conventional O-ring seals. The 5500+ °F combustion gases are kept a safe distance away from the seals by thick layers of phenolic or rubber insulation. Special joint-fill compounds are used to fill the joints in the insulation to prevent a direct flow-path to the seals. Normally, these two stages of protection are enough to prevent a direct flowpath of the 900-psi hot gases from reaching the seals. Occasionally, seals have experienced charring due to parasitic leakage paths that open up in the

*Senior Research Engineer, Mechanical Components Branch, Member AIAA.

†Research Engineer.

Copyright © 1999 by the American Institute of Aeronautics and Astronautics, Inc. No copyright is asserted in the United States under Title 17, U.S. Code. The U.S. Government has a royalty-free license to exercise all rights under the copyright claimed herein for Governmental Purposes. All other rights are reserved by the copyright owner.

joint-fill compounds during rocket operation. Inspection during disassembly of Space Shuttle solid rocket motor nozzle joints from RSRM-44 and RSRM-45 revealed O-ring erosion of Joint 3 primary O-ring seals⁴ (Fig. 1). Subsequent improvements in joint-fill compound application-techniques have apparently overcome the Joint 3 charring problem. However, a number of nozzle joints including the nozzle-to-case joint and Joint 2 continue to show hot gas penetration through the joint fill compound. The current nozzle-to-case joint design incorporates primary, secondary and wiper (innermost) O-rings and polysulfide joint-fill compound. In the current design, 1 out of 7 motors experience hot gas to the wiper O-ring. Though the condition does not threaten motor safety, evidence of hot gas to the wiper O-ring results in extensive reviews before resuming flight. NASA and solid rocket motor manufacturer Thiokol are working to improve the nozzle-to-case joint design by implementing a more reliable J-leg design and a thermal barrier, and eliminate the joint-fill compound (Fig. 1). The J-leg is molded into the insulation and contacts the mating surface of the adjoining element. Rocket pressurization acts to further preload the J-leg increasing its effectiveness. The basic J-leg design has been applied successfully to fixing the field joints in the redesign effort following the Challenger accident.⁵ The thermal barrier, compressed between the J-leg and adjoining element, is intended to resist any hot gases the J-leg does not block and prevent them from reaching the wiper O-ring. The braided carbon thermal barrier being developed at NASA Glenn is the leading candidate based on the results presented herein.

The thermal barrier for the Shuttle solid rocket motor has unique requirements, including the following, amongst others:

1. Sustain extreme temperatures (2500 to 5500 °F) during solid rocket motor burn (2 min and 4 sec.) without loss of integrity.
2. Drop incoming gas temperatures (up to 3200 °F) in the joint to levels acceptable to Viton O-rings (≤ 600 °F, short-term) to prevent O-ring damage, including char and erosion.
3. Exhibit some permeability to permit the joint cavity (between thermal barrier and O-ring) to reach chamber pressure (900-psi) in acceptable time.
4. Exhibit adequate resiliency/springback to accommodate limited joint movement and manufacturing tolerances in these large (8.5 ft. diam.) nozzle segments.
5. Diffuse/spread incoming narrow (0.08 in. diam.) hot gas jets to reduce their damaging effects on the downstream O-rings.
6. Block hot slag (i.e., molten alumina, etc.) entrained in gas stream from reaching O-rings.

Steinetz and Dunlap³ performed a number of tests on 0.125- and 0.200-in. diameter braided carbon-fiber thermal barriers demonstrating that they met the burn-resistance, permeability, and resiliency criteria.

The main objective of the current study is to fully characterize two braided carbon fiber thermal barrier designs (denoted Carbon-3 and Carbon-6) by assessing their transient thermal response when subjected to a high temperature torch and by characterizing their permeability, resiliency, and burn-resistance. The Carbon-6 design is currently being tested by both NASA and Thiokol for the nozzle-to-case joints of the Shuttle solid rocket motor. Subscale rocket “char” motor tests were performed to assess the thermal barrier’s (Carbon-6) thermal response and heat resistance under actual rocket conditions.

Test Apparatus and Procedures

Thermal Barrier Specimens

Carbon-3 and Carbon-6 were subjected to burn, temperature drop, flow, and compression tests. Carbon-6 was also tested in a subscale char motor. Limited testing was performed on the Carbon-4 design. Table I summarizes the relevant architecture parameters for the thermal barrier designs that were tested.

All thermal barriers were composed of a uniaxial core of fibers overbraided with various numbers of sheath layers. The Carbon-6 design had ten sheath layers and a 0.26-in. diameter. Carbon-6 had good flexibility and compliance properties because it was braided with a more open architecture. The Carbon-3 design had a 0.20-in. diameter and was made with a large degree of uniaxial core fibers overbraided with five sheath layers. Carbon-3 was a tight braid that was not as flexible as Carbon-6. Carbon-4 had 4.4×10^{-4} in. (11 μm) pitch-based Amoco P25 fibers in its core to evaluate core fiber diameter effects on performance, while the core fibers of all the other carbon thermal barriers were 2.76×10^{-4} in. (6.9 μm) PAN-based Grafil type 34-700 fibers. PAN-based Thornel T-300 carbon fibers with a 2.8×10^{-4} in. (7 μm) diameter were used in the sheaths of all the thermal barrier designs.

Thermal Barrier Porosity Measurements

To assess thermal barrier porosity while under compression, samples of the Carbon-3 and Carbon-6 designs were examined in a compressed state using a photographic stereomicroscope. Four 1/2-in. long specimens of both types of thermal barriers were prepared and weighed using a precision electronic balance. The exact length of each specimen was measured using vernier calipers. Each specimen was then clamped between two steel plates and subjected to a 20% compression. While the specimens were compressed, a light layer of cyanoacrylic glue was applied to the surface

of each specimen so that they would maintain their compressed shape upon removal from the fixture.

Four specimens were examined for both Carbon-3 and Carbon-6. Both ends of each specimen were examined and photographed at 10X in the microscope so that eight cross section photos were examined for both thermal barrier designs. Each cross section assumed an ellipsoidal shape in its compressed state. The dimensions of each ellipse were measured using vernier calipers. These dimensions were then used to calculate the cross sectional area of both ends of each specimen. An average cross sectional area was calculated for each specimen and multiplied by the specimen length to determine the specimen volume. Specimen density was then calculated by dividing the weight of the specimen by its volume. An average density at 20% compression was found for both Carbon-3 and Carbon-6 by averaging the densities of the four specimens of each design. The porosity of each thermal barrier design at 20% compression was calculated using the following relationship:

$$\text{Porosity} = 1 - \left(\rho_{\text{Thermal Barrier}} / \rho_{\text{Carbon Fiber}} \right)$$

In this relationship, the density of each thermal barrier design was divided by the density of an individual carbon fiber (0.064 lb/cu.in.). Thus, a thermal barrier design would have a porosity of zero if it had no gaps and assumed the density of an individual fiber.

Burn Tests

A screening test was developed to evaluate thermal barrier burn resistance under simulated rocket motor combustion temperatures (5500 °F) by aiming a “neutral” flame⁶ of an oxyacetylene welding torch at the center section of a 4-in. thermal barrier specimen. In these tests, the amount of time required to completely cut through the specimen was measured. Time for cut-through was measured from the instant the flame touched the specimen until the specimen was completely cut into two separate pieces. A detailed description and an illustration of the fixture used to perform these tests can be found in the paper by Steinetz and Dunlap.³

Temperature Drop Tests

A test fixture was developed to measure the temperature drop across and along the thermal barriers in a compressed state when subjected to the neutral flame of an oxyacetylene torch simulating rocket temperatures (Fig. 2). Flow was drawn through the thermal barrier using a vacuum roughing pump to lower pressure on the downstream side of the thermal barrier while leaving the upstream side at ambient conditions. Flow through the thermal barrier was measured using a flow meter positioned between the fixture and the roughing pump. The volume

downstream of the thermal barrier was an enclosed plenum chamber sealed by an O-ring between the bottom plate and a top plate. The thermal barrier was compressed at 20% linear compression. Other compressions are possible by placing shims under the thermal barrier. The fixture was made out of phenolic insulation having low thermal conductivity that simulates the solid rocket motor insulating material and minimizes parasitic heat loss.

The torch flame was applied to the thermal barrier to simulate a leak path of hot gases through the nozzle joint. The flame with temperatures up to 3200 °F was positioned on a small area of the thermal barrier. An “iris plate” with a 0.084-in. diameter hole concentrated a “laser-like” column of flame onto the thermal barrier, simulating a hot gas jet flowing through the rocket nozzle joint. The iris plate was positioned about 1/4-in. away from the specimen. The jet was directed at the center of the specimen both span- and height-wise.

To measure the surface temperature distribution along the thermal barrier span, thermocouples were placed on both the upstream (hot) and downstream (cold) sides. The thermal barrier specimen sat between these two rows of thermocouples in a 0.040-in.-deep groove. The thermocouples measured how the flame spread along the thermal barrier, how much temperature drop occurred across the thermal barrier, and how heat was conducted along its length. The fixture was instrumented with seven thermocouples upstream of the thermal barrier and eight downstream thermocouples. On the upstream side, the center Type B thermocouple was placed directly in line with the center of the hole in the iris plate so that it measured the hottest flame temperature at the surface of the thermal barrier. Type B thermocouples were then positioned 1/4-in. on either side of the center thermocouple (Fig. 2). The remaining four thermocouples on the hot side were Type K thermocouples, and they were placed 1/2 and 1 in. on either side of the center thermocouple. Seven of the eight Type K thermocouples downstream of the thermal barrier were spaced so that they were directly in line with those upstream of the thermal barrier. The remaining Type K thermocouple was positioned 1/4 in. (approximately one thermal barrier diameter) downstream of the thermal barrier in line with the center thermocouple and measured the bulk air temperature.

Thermocouple selection. Fine gage wire open-bead thermocouples were used to quickly and accurately measure changes in the surface temperature distribution along the thermal barrier. The time constant and response rate of a thermocouple is controlled by the size of its wires and the diameter of the junction ball that is formed between the wires. The wire diameters used for the Type B and Type K thermocouples were 0.010 and 0.0125 in., respectively. A typical thermocouple junction ball has a diameter about 50% larger than the wires in the thermocouple. Calculations

of the time constants for junction balls with a diameter of 0.015 to 0.019 in. showed that these thermocouples would have a time constant of about 1/2 sec.

Pressure/Flow Transducers. An absolute pressure transducer measured the pressure upstream of the thermal barrier while a differential transducer measured the pressure drop across a specimen. Flow through the thermal barrier was measured using a 0 to 100 SLPM flowmeter. Data was acquired from all of this instrumentation at a sampling rate of 10 Hz using Keithley data acquisition hardware and Labtech Notebook software.

For each test, a 5-in. thermal barrier specimen was prepared and installed into the groove in the fixture. The 14 thermocouples that measured the surface temperature along the specimen were slipped into the outer sheath layer of the thermal barrier and adjusted so that they were spaced properly. To prevent parasitic leakage, the plenum chamber O-ring was then positioned so that it was snug against the ends of the thermal barrier. The vacuum pump was turned on for several minutes, to cause the pressure drop and to achieve a steady flow rate through the specimen before applying the torch. The oxyacetylene torch was adjusted until a neutral flame was formed. The torch was slid along a machined groove until it was properly positioned in front of the hole in the iris plate. The torch was left on the specimen for 30 or 60 sec. and then pulled away from the fixture and shut off. Sometimes repeat tests were performed on the same specimen to examine the effects of repeated flame exposures. Torch nozzle spacing to the iris plate proved to be important in controlling the maximum hot side temperature without melting the center Type B thermocouple (platinum-rhodium, $T_{\text{melt}} = 3308$ °F). Torch spacings for Carbon-3 and Carbon-6 were 0.265 and 0.160 in. respectively.

Flow Tests

Flow tests were performed on the thermal barriers in a high temperature flow and durability test rig shown schematically in Fig. 3. The test rig is capable of operating at temperatures from room temperature to 1500 °F, pressures between 0 and 100 psig, and flows of 0 to 3.5 SCFM (standard cubic feet per minute, conversion 1 SCFM = 28.3 SLPM). Specimen length was 7.50 ± 0.05 in., and the thermal barriers were mounted into a groove in the piston. The free ends of the specimens were joined together in the piston groove using a 1/4 in. lap joint. Preload was applied to the specimens through a known interference fit between the thermal barrier and the cylinder inner diameter. To vary the amount of preload, the interference fit was modified by mounting different thicknesses of stainless steel shims behind the specimen in the piston groove. During flow testing, hot pressurized air entered at the base of the cylinder and flowed to the test specimen that sealed the annulus created by the cylinder and piston walls (0.007 in.

radial gap). The durability of the thermal barriers at high temperatures was examined by subjecting them to scrub cycles in which the piston and thermal barrier were reciprocated in the cylinder.

Flow data was recorded before scrubbing at temperatures of 70 and 500 °F and after scrubbing at 70, 500, and 900 °F. Specimens were subjected to ten scrub cycles at 500 °F. At each temperature, flow data was recorded at pressures of 2, 5, 10, 30, 60, 90, and 100 psid (or as high as could be recorded within the limits of the flowmeters) with the downstream pressure at ambient pressure. Primary and repeat flow tests were performed on the Carbon-3 and Carbon-4 designs for a diametral or linear compression of 0.040 and 0.050 in. (20 and 25% linear compression) and on the Carbon-6 design at linear compressions of 0.052 and 0.065 in. (20 and 25% linear compressions). A detailed description of the hardware and procedure used to perform these tests can be found in the papers by Steinetz et al.¹ and Steinetz and Adams.²

Compression Tests

Compression tests were performed to determine thermal barrier preload and resiliency behavior at room temperature using a precision linear slide compression test fixture shown schematically in Fig. 4. A 1 1/2-in. long specimen was loaded into a stationary grooved specimen holder, and an opposing plate was compressed against the specimen. Stainless steel shims were placed in the groove behind the specimens to vary the amount of linear compression. The amount of compressive load on the specimen was measured versus the amount of compression. Multiple load cycles were applied to the specimen before the preload data point was recorded to remove effects of the hysteresis and permanent set that accumulate with load cycling of the specimens. Most permanent set occurred within the first four load cycles. A pressure sensitive film mounted on the opposing plate was used to determine the contact width of the specimen as it was compressively loaded. The footprint length (nominal 1 in.) and width at the end of the fourth load cycle were used along with the measured load versus compression data to calculate the estimated preload and residual interference corresponding to a given linear crush value.¹ Residual interference is defined as the distance the specimen will spring back while maintaining a load of at least 1 lb/in. of specimen.

Compression tests were performed on the Carbon-3 and Carbon-6 designs to determine the specimen preloads corresponding to the linear crushes used in the flow experiments. Tests were performed at compressions of 20, 25, and 30% of each specimen's overall diameter. Primary and repeat compression tests were performed. The hardware and procedure used to perform these tests are described in detail by Steinetz et al.¹

Subscale Rocket “Char” Motor Tests

As part of the development process of the thermal barrier, Thiokol Corporation performed tests using a subscale (70 lbm) rocket “char” motor. In these tests, the NASA Carbon-6 0.260-in. cross-sectional diameter thermal barrier impeded hot gas flow through an intentional circumferential defect between rocket-case insulation blocks. The thermal barrier compression was 20%. The insulation blocks were modified to accommodate a 5 1/8-in. diameter thermal barrier. The 0.060-in. defect was much larger than any defects that would normally form through the gap-fill material in the actual rocket nozzle joint, but this size was chosen to force gas flow through the thermal barrier under very extreme conditions. Burning solid rocket propellant, the rocket fired for 11 sec. and generated 900 psi pressures and 5000 °F (estimated) chamber temperatures. Hot gas flowed to the thermal barrier while upstream and downstream temperatures and pressures were recorded. The char motor incorporated an outboard plenum chamber, or reservoir, to simulate the volume (80 in.³) between the thermal barrier and the Viton O-ring seals. This reservoir ensured that flow would pass through the thermal barrier. The reservoir started at ambient pressure and then quickly reached chamber pressure, simulating the actual RSRM joint fill-time. After the volume between the thermal barrier and Viton O-ring pressurizes in the rocket nozzle joint, charring risk to the Viton O-ring is virtually eliminated.

Results and Discussion

Thermal Barrier Porosity Measurements

Measured values for thermal barrier density and porosity at 20% compression are presented in Table II for the Carbon-3 and Carbon-6 thermal barrier designs. A 20% compression level was chosen, as this is the compression level selected for the nozzle-to-case joint thermal barrier. The densities/porosities of braided structures are important for understanding their thermal and flow response characteristics.

Carbon-3 had a higher density (0.041 lb/cu.in.) and a lower porosity (0.37) than did Carbon-6 (0.032 lb/cu.in. and 0.50, respectively). This can be attributed to the differences in braid architecture between these two designs as shown in Table I. Carbon-3 had a core composed of ten uniaxial 12K yarns of Grafil 34-700 carbon fibers—a large fraction of its cross-section, while Carbon-6 only had one 12K yarn in its core. Carbon-6 had ten sheath layers of braided carbon fibers, while Carbon-3 only had five layers. Carbon-6 also had a lower sheath braid angle and fewer carriers per sheath layer to produce a softer, more flexible thermal barrier. Because the uniaxial fibers in the core pack together much better than the braided fibers that cross over each other in the sheath, the Carbon-3 design with a

greater percentage of core fibers is naturally more dense and less porous. Steinetz and Dunlap³ showed previously that the density of a braided carbon thermal barrier was inversely related to the number of sheath layers.

Burn Test Results

The amount of time to burn through each type of thermal barrier is shown in Fig. 5. In this figure, the number of specimens that were tested is given next to the name of each thermal barrier type, and the average burn-through time is found above each bar. As shown previously by Steinetz and Dunlap,³ carbon fiber thermal barriers were the most burn-resistant. Figure 5 summarizes the earlier tests done on 1/8-in. diameter stainless steel rods, Viton O-rings, and all-ceramic braided rope seals. It also shows the burn times of the 1/8-in. diameter (Carbon-1, Carbon-2, and Carbon-2A) and 0.200-in. diameter (Carbon-3 and Carbon-4) carbon thermal barriers as well as new data on the burn time of the 0.260-in. diameter Carbon-6 design. The 1/8-in. diameter designs all endured the 5500 °F oxyacetylene torch for about 2 min. Even more impressive burn times were seen for the 0.200-in. diameter designs at about 6-1/2 min. This is more than three times the Shuttle solid rocket motor burn time of 2 min, 4 sec. However, an increase in diameter to 0.260 in. did not produce an increase in burn time. Carbon-6 at 0.260 in. in diameter had a similar burn time to the 0.200-in. diameter designs at about 6-1/2 min. Like the other carbon thermal barriers, Carbon-6 was soft and flexible after removal from the flame, even in the area affected by the flame, with no evidence of charring or melting. All of the non-carbon specimens showed signs of charring or melting after removal from the flame, and many became very brittle in the area that was burned.

The similarity in burn time between Carbon-6 and the smaller-diameter Carbon-3 and Carbon-4 thermal barriers is believed to be related to the difference in porosity between these designs. As shown in Table II, Carbon-6 is more porous than Carbon-3 even in a compressed state. Steinetz and Dunlap³ theorized that the mass-loss mechanism during the oxyacetylene torch tests was carbon oxidation. Depending on material type, carbon fibers begin to oxidize at temperatures in the range of 600 to 900 °F.⁷⁻⁹ The oxyacetylene torch burning at 5500 °F is hot enough to cause oxidation to occur, but too cool for carbon sublimation that occurs at 6900 °F.¹⁰ It is believed that the looser, more porous braid of Carbon-6 allowed more of the hot, oxidizing torch flame to pass through it. This allowed oxidation to occur more rapidly in the innermost fibers of Carbon-6 than in the less porous Carbon-3 design. Even though there were more carbon fibers in the larger Carbon-6 design, they were cut through more quickly because they were exposed sooner to hot, oxidizing gases. These results indicate that burn/oxidation

resistance is dependent on both thermal barrier diameter and porosity.

Products of combustion in the solid rocket motor include liquid alumina (Al_2O_3) and gaseous CO , ClO_2 , Cl , HCl , and H_2 , none of which are oxidative. Hence, it is believed that the neutral flame in ambient air (oxidizing) is a conservative (i.e., more aggressive) environment for performing material screening burn tests. It is expected that oxidation rates within the rocket environment will be slower than those exhibited herein.

Temperature Drop Test Results

Temperature drop tests were performed on the Carbon-3 and Carbon-6 thermal barrier designs using the test fixture described that measured the temperature drop across and along the thermal barrier in a compressed state when subjected to the flame of an oxyacetylene torch. Figure 6 shows temperature versus time traces for a test performed on a Carbon-3 specimen. Data recorded from the center thermocouple and the three thermocouples to the right of center on both the hot and cold sides of the specimen are presented. Data from the thermocouples to the left of the center thermocouple is not shown in this figure for clarity. In general, the left and right sides produced symmetric data. Also shown in the figure is the temperature trace from the “cold bulk” (T_{bulk}) thermocouple that measures the air temperature 1/4 in. downstream of the specimen. For sensitivity purposes, we moved the T_{bulk} thermocouple spatially to see if we were missing any local “hot-streaks,” and we did not find any. Figure 7 shows temperature traces for a test performed on a Carbon-6 specimen.

Examining Figs. 6 and 7, it can be seen that the center thermocouple on the hot side (T_{hot}) and the center thermocouple on the cold side (T_{cold}) of the thermal barrier each recorded the hottest temperatures on their respective sides. This is expected as these thermocouples are directly in line with the hottest part of the torch flame as it passes through the hole in the iris plate. These figures also show that the temperature got progressively cooler from the center thermocouple to the R1, R2, and R3 thermocouples on the hot and cold sides of the specimen. This was also expected as the temperature decayed with movement further away from the center heat source.

Figures 6 and 7 show that there was a lag between increases in temperature on the hot and cold sides of the specimen. When the torch was applied to the thermal barrier, the hot side thermocouples instantly registered the increase in temperature. The insulating properties of the thermal barrier delayed heat conduction to the cold side, so the cold side thermocouples did not register an increase in temperature until several seconds after the torch was applied. The cold side temperatures measured were significantly lower than the hot side temperatures, as will be

discussed below. After the torch was pulled away from the specimen, the hot side thermocouples instantly showed a decrease in temperature. The cold side thermocouples, though, continued to increase for 3 to 5 sec before beginning to decrease in temperature. Comparing the hot side temperatures in Figs. 6 and 7, one notes fluctuations in temperature for Carbon-6 but not Carbon-3. The origin of this fluctuation is unclear at this point, but we could find no system source of the variation (e.g. thermocouple integrity, etc.).

Figure 8 shows the temperature drop across specimens of Carbon-3 and Carbon-6 for flame applications of ~30 sec. The temperature drop was calculated as the difference between the temperature recorded by the hot side center thermocouple and the cold side bulk temperature (T_{bulk}). Over the 30-sec. torch application, the temperature drop across the Carbon-3 specimen dropped from a high of 2870 to 2680 °F by the end of the test. This drop was caused by a steady rise in the cold side bulk temperature while the hot side temperature remained nearly constant. Carbon-6 exhibited a temperature drop in the range of 2980 to 2600 °F. The uneven nature of the Carbon-6 trace is due to fluctuations in the hot side temperature, as noted above. As shown by these figures, both Carbon-3 and Carbon-6 thermal barrier designs caused a comparable temperature drop across the thermal barrier over a 30-sec. torch flame application.

Figure 9 illustrates the symmetry of the temperature drop data for Carbon-3 and Carbon-6. Figure 9(a) shows the temperatures recorded by the seven hot and cold side thermocouples that were in contact with the surface of a Carbon-3 specimen 15 sec. into the test. Though the downstream volume in the nozzle-to-case joint of the Shuttle solid rocket motors is expected to fill in <10 sec., 15 sec. was chosen to include a safety factor of 5 sec. Figure 9(b) shows similar data for a test performed on Carbon-6. Both figures show the temperature distribution from left to right across the hot and cold sides of the thermal barriers. The center thermocouples on the hot and cold sides correspond to a position of zero. Thermocouples to the left of center have a negative position value, while those to the right have a positive value. Both figures show a temperature distribution that is close to symmetric around the center thermocouples. Figure 9(a) shows that the data for this Carbon-3 test is shifted slightly to the right. Both figures show a temperature drop of about 2300 °F between the hot (T_{hot}) and cold (T_{cold}) center thermocouples in contact with the surface of the specimens.

Jet Spreading. The jet spreading capability of Carbon-3 and Carbon-6 is also shown in Fig. 9. Although the hot (3000+ °F) torch was focused into a narrow (0.084-in. diam.) column, the thermal barrier spread the heat at least 1 in. on either side of the center thermocouples. Figure 9(a) shows that for Carbon-3, temperatures 1/4 in. away from the center hot side thermocouple were about

1200 °F on the left side and over 2000 °F on the right side. Hot side data for Carbon-6 in Fig. 9(b) show a similar trend with temperatures 1/4 in. away from center over 2200 °F. Cold side data from both Figs. 9(a) and (b) show that the hot gas jet was reduced in temperature and diffused. Reducing the unit thermal energy per area is beneficial in preventing hot gas effects on the downstream O-rings.

Focused Jet Endurance Tests. Table III and Fig. 10 summarize the results of repeated temperature drop tests performed on single specimens of Carbon-3 and Carbon-6 to examine their endurance after multiple applications of the oxyacetylene torch. For both thermal barrier designs, a single specimen was subjected to the torch flame for two 30-sec. periods followed by two 60-sec. periods. The exposure times of 30 and 60 sec. are longer than the joint cavity fill time of 10 sec. but were selected to examine the thermal barrier's insulation and flame resistance properties. After each exposure, the specimen was photographed (with fixture cover plate removed) to record any specimen damage before the next test was performed. For reference, the Carbon-6 specimen was also exposed to a 20-sec. flame application before these endurance tests, and no damage was observed.

Table III shows several important temperature measurements for each test after 15 sec. as well as the flow through the specimen at fifteen seconds, the maximum bulk temperature reached during a test, and the amount of recession on the hot side of the specimen after the final flame exposure. The data for Carbon-3 shows that tests 30, 31, and 32 were almost identical. Each showed a maximum hot side temperature slightly above 3000 °F and a temperature drop ($T_{\text{hot}} - T_{\text{bulk}}$) of over 2800 °F. The only difference between these tests was the higher maximum bulk temperature of 500 °F in test 32. This was due to the longer flame exposure time that allowed the bulk temperature to keep increasing for 60 sec as compared to the 30-sec exposures in tests 30 and 31. The maximum hot side temperature in test 33 only reached 2590 °F compared to 3000+ °F in the other tests. This caused lower temperature differences across the specimen and lower bulk temperatures. For all four tests, the highest bulk temperature after 15 sec. was 230 °F. This is well below Viton's short term maximum operating temperature limit of 600 °F.¹¹ Even the maximum bulk temperature of 500 °F recorded after 60 sec. of flame exposure was within the limit. Figure 10(a) shows the hot side of the Carbon-3 specimen after all four flame exposures. No damage can be seen after the first three tests with little if any damage evident after the final test. As shown in Table III, there was a recession of 0.029 in. (13% of the compressed cross-section) measured after 180 sec. of exposure. The thermal barrier should never experience such a prolonged exposure to jets of hot gas in the actual rocket application.

The endurance tests performed on Carbon-6 revealed results slightly different than for Carbon-3. After 15 sec., the maximum temperature ranged from 2520 to 2730 °F with temperature drops ($T_{\text{hot}} - T_{\text{bulk}}$) that ranged from 2240 to 2560 °F. The maximum bulk temperature after 15 sec. was 280 °F, slightly higher than that for Carbon-3 but still well below the Viton O-ring temperature limit. The Carbon-6 series revealed a slightly higher maximum overall bulk temperature of 620 °F that occurred in the final test after a 60-sec. flame exposure. This temperature is about the maximum that the O-rings can withstand for a short period of time, but as mentioned previously, the thermal barrier should not experience such a long flame exposure in the rocket.

Figure 10(b) shows the hot side of the Carbon-6 specimen after all four flame exposures. Very little damage can be seen after the first test, but the amount of damage to the specimen increased to a maximum recession of 0.092 in. (30% of the compressed cross-section) after the final test. This recession likely contributed to the increased maximum bulk temperature in the final test. These temperature drop tests were all performed in a more aggressive oxidizing environment than the thermal barrier would experience in the rocket. The amount of damage observed on the Carbon-6 specimen after 200 sec. of flame exposure would not be expected to occur in a less oxidizing environment with much shorter hot gas exposures.

For both series of tests, the flow through the specimen was almost identical from test to test. Flow rates through Carbon-6 were higher than those through Carbon-3 as is expected since Carbon-6 is more porous than Carbon-3 (Table II).

Flow Test Results

Flow rates (measured using the piston flow rig, Fig. 3) for Carbon-3, Carbon-4, and Carbon-6 at 20 and 25% linear compression are summarized in Fig. 11 at 60 psid and 70, 500, and 900 °F after scrubbing and 70 °F before scrubbing. Application of the thermal barrier in the Shuttle solid rocket motor nozzle-to-case joint involves predominantly static (e.g. no scrubbing) loads. As shown by the flow results, flow resistance increased with higher compression levels. Figure 11 shows that the flow rates for Carbon-6 were higher than those for Carbon-3 and Carbon-4 at 60 psid at each temperature and compression level. Carbon-6 flow rates were 2.1 to 2.9 times higher than Carbon-3 flow rates and 1.7 to 2.3 times higher than Carbon-4 flow rates at comparable temperatures and compression levels. This difference is due to differences in braid architecture between these thermal barrier designs. The difference in flow rates between Carbon-3 and Carbon-4 was attributed to Carbon-4 incorporating larger core fibers resulting in higher seal porosity than Carbon-3.³ Carbon-6 incorporating multiple sheath layers

has a higher porosity than Carbon-3 (Table II) and is therefore more permeable. Discussions between the authors and rocket manufacturer Thiokol have indicated that the thermal barriers have high enough permeability to permit the joint-cavities to fill in acceptable times.

Effect of Temperature. Figure 11 shows that flow rates dropped for each thermal barrier as the temperature was increased. This phenomenon is explained by the relationship that gas viscosity increases with temperature, $\mu \propto T^{2/3}$. Thus, as the viscosity of the gas flowing through the thermal barriers increased, the flow rate decreased.²

Effect of Hot Scrubbing. Thermal barrier flow rates typically rose after hot scrubbing during flow tests. After 500 °F testing Carbon-6 flow rates rose as much as 20% as compared to the flow rates before scrubbing. Post-scrub room temperature flows for all thermal barriers were done after time spent at 500 °F (2 hr) and 900 °F (1.5 hr). Post-scrub room temperature flow rates for Carbon-3 as much as doubled as compared to their pre-scrub values. Carbon-6 exhibited similar flow growth after scrubbing but flows for pressure differentials of 60 psid were not within the range of the flow meter used. It is believed that much of the flow rate increase is due to oxidation that occurred while the specimen soaked at these high temperatures. No major visible damage due to scrubbing was observed on any of the thermal barrier designs at the conclusion of the flow tests. Only minor fraying was observed at the specimen ends in the lap joint. Temperature exposure tests performed on carbon fiber thermal barriers³ showed that short lengths of carbon thermal barrier lost weight when heated in a furnace at different temperatures for two-hour exposures. This supported the theory that the carbon thermal barriers oxidized when exposed to temperatures of 900 °F for extended periods of time, and the associated weight-loss contributed to the increased flow rates after scrubbing.

Compression Test Results

Table IV summarizes the results of the compression tests performed on Carbon-3 and Carbon-6 and includes the measured contact width, preload, and residual interference for each amount of linear compression, or crush, tested.

Contact Width. The contact width increased for the Carbon-3 and -6 designs as the amount of linear crush was increased. The thermal barriers continued to spread and flatten out as they experienced larger amounts of compression. In each test, the footprint pattern left on the pressure sensitive film after a compression cycle was solid and continuous. This indicates that during a flow test continuous contact is made between the walls of the flow fixture and the thermal barrier, minimizing leakage past the specimen.

The contact width at each compression level for Carbon-6 was over twice as large as it was for Carbon-3 even though the diameter of Carbon-6 was only 1.3 times larger than for Carbon-3. This shows that Carbon-6 had a softer, more compressible braid architecture than Carbon-3 allowing Carbon-6 to spread out more as it was compressed.

Preload. The amount of preload or footprint contact pressure increased with the amount of linear crush. However, Carbon-6 had preloads that were 1/6th to 1/9th those for Carbon-3 at each compression level. As a result, Carbon-6 will cause lighter loads on the adjoining rubber J-leg element. The reason for this difference in preload is believed to be related to the architectures of these thermal barrier designs (Table I). In Carbon-3 having a tightly packed core of uniaxial fibers, there is little room for individual fibers to move with respect to one another when they are compressed. In contrast, in Carbon-6 the sheath fibers are oriented at an angle with each other and are better able to slide past each other when the thermal barrier is compressed.

Residual Interference. As with the contact width and preload, thermal barrier residual interference or spring back also increased as percent linear crush increased. Although contact width and preload were quite different for Carbon-6 and Carbon-3, residual interference scaled with diameter for these two designs. Increasing thermal barrier diameter by a factor of 1.3 from 0.200 to 0.260 in. resulted in an increase in residual interference by that ratio for each level of compression. Residual interference for Carbon-6 was 0.025 in. even for the lowest compression (20%) and meets the design requirement to follow nozzle joint movement during Shuttle solid rocket motor operation, as discussed with rocket manufacturer Thiokol.

Comparison of Carbon-3 and Carbon-6: Other Factors

Carbon-3 and Carbon-6 both performed well in the temperature drop comparison tests. Carbon-3 did offer somewhat greater insulating effects than Carbon-6 and showed less recession than Carbon-6. We believe the higher density of Carbon-3 is an important reason for these results. However, there are many other factors to consider when deciding between these two braid architectures. Carbon-6 is braided using larger tows or yarns that permits faster and therefore most cost-effective production. Carbon-6 is a more flexible braid that makes it easier to spool for shipment and more accommodating during installation. The current tests combined with other planned rocket motor and joint-simulation tests will enable Thiokol and NASA to decide on the optimal braid architecture for the thermal barrier.

Results of Thiokol Char Motor Tests on Carbon Thermal Barrier

Thiokol tested a 0.260-in. diameter Carbon-6 thermal barrier for NASA in a subscale rocket motor to verify that it would withstand the Shuttle solid rocket motor environment. The subscale motor, or “char” motor, simulates the thermal conditions of the full-scale motor by burning solid rocket propellant at corresponding chamber pressure and temperature conditions. The thermal barrier was placed into an intentional gap defect between the phenolic insulation blocks, as shown in Fig. 12(a). The combination of an outboard plenum chamber and the 0.060-in. circumferential gap extending both upstream and downstream of the thermal barrier ensured that hot gas flow would pass through the thermal barrier.

Throughout the test duration of ~11 sec., a significant drop in temperature was measured across the thermal barrier. Figure 12(b) shows that the maximum temperature seen on the hot side of the thermal barrier was over 3200 °F, while the cold side temperature reached about 950 °F. Thus, a temperature drop of about 2200 °F occurred across the 0.260-in. diameter thermal barrier. Pressure readings upstream and downstream of the thermal barrier and in the reservoir confirmed that there was gas flow across the thermal barrier. The thermal barrier diffused the focused nature of the hot gas jet, further reducing the jet’s potentially damaging effects on downstream Viton O-rings in the actual Shuttle solid rocket motor.

Although the 950 °F temperature recorded downstream of the thermal barrier is still higher than the temperature limits of the Viton nozzle O-rings, the char motor subjected the thermal barrier to more aggressive conditions than would ever occur in the actual Shuttle solid rocket motor, for the following reasons. First the gap defect was purposely oversized at 0.060 in. to force flow through the thermal barrier. In the actual nozzle joint, the gap between adjoining blocks of insulation would be narrower as the pieces of insulation are basically in contact with each other. The narrow gaps between the phenolic insulation would significantly cool the incoming gas temperature impinging on the thermal barrier and would therefore lower the temperature of the gas that reaches the Viton O-rings. Furthermore, the downstream temperature in the char motor test was recorded immediately downstream of the thermal barrier. The O-rings in the rocket nozzle joint are located several inches further downstream of the thermal barrier, allowing additional heat to be removed from the gas before reaching the O-rings.

Figure 13 shows the thermal barrier after it was removed from the char motor. There was no apparent burning or charring of the thermal barrier. In addition, Fig. 13 shows that the thermal barrier also acted as an

effective slag barrier. The inset photo in the figure shows a close-up of an area where slag was trapped by the thermal barrier, preventing it from reaching the downstream O-rings. Minor fraying occurred in the area immediately around the lap joint during disassembly, but the specimen is otherwise in good condition.

Comparison of Thiokol Char Motor Test Results to NASA Temperature Drop Test Results

The fixture used to perform the temperature drop tests on the Carbon-3 and Carbon-6 thermal barriers was modelled after the char motor and the shuttle nozzle-to-case joint thermal conditions. The fixture was made out of phenolic material to simulate the material and boundary conditions that the thermal barrier would be exposed to in these other configurations. The thermal barrier specimens were subjected to 20% compression as they were in the char motor test and as planned for the rocket. The flame of the oxyacetylene torch that was used for the temperature drop tests was directed through a 0.084-in. diameter hole in an iris plate to simulate a hot gas jet that the barrier could be exposed to in the rocket. Flame exposure times were intentionally longer than they would be in the rocket application to simulate extreme heating conditions.

Considering the results of Fig. 10 (NASA temperature drop fixture), tests were performed with hot side temperatures ranging from 2500 to nearly 3200 °F. Carbon-6 temperature drops ranged from 2240 to 2560 °F–15 sec. into the test. These were somewhat greater than the 2200 °F temperature drop exhibited by Carbon-6 in the char motor. The main reason for this difference is that 900 psi pressures were generated by the char motor, while only 10 psid pressures were applied across the thermal barrier in the temperature drop tests. The higher-pressure char motor test caused more hot gas to flow through the thermal thereby raising the downstream temperature causing a smaller temperature drop. Though there are some differences in the absolute results, the authors believe the laboratory temperature-drop test fixture simulates many of the key factors at work in the rocket. The laboratory set-up permits quick and easy comparisons between competing architectures and can be used to generate thermal data to anchor thermal correlations under development.

Summary and Conclusions

The 5500+ °F combustion gases in the Space Shuttle solid rocket motor are kept a safe distance away from the assembly joint seals by thick layers of insulation and by special compounds that fill the joint split-lines in the insulation. The current nozzle-to-case joint design incorporates primary, secondary and wiper (innermost) O-rings

and polysulfide joint-fill compound. In the current design, 1 out of 7 motors experience hot gas to the wiper O-ring. Though the condition does not threaten motor safety, evidence of hot gas to the wiper O-ring results in extensive reviews before resuming flight. NASA and solid rocket motor manufacturer Thiokol are working to improve the nozzle-to-case joint design by implementing a more reliable J-leg design (successfully used in the field and igniter joints) and the thermal barrier Carbon-6 described herein.

The thermal resistance of two NASA thermal barriers, denoted Carbon-3 and Carbon-6, was assessed by exposing them to an oxyacetylene torch at 5500 °F and measuring time for burn through. Temperature drop tests were performed to measure the temperature drop across and along the thermal barriers in a compressed state when subjected to the flame of an oxyacetylene torch. Flow and durability tests were conducted on the thermal barriers to examine their leakage characteristics and durability at ambient and high temperatures. Room temperature compression tests were performed to determine load versus linear compression, preload, contact area, and residual interference/resiliency characteristics. Subscale rocket “char” motor tests were performed in which hot combustion gases were directed at the Carbon-6 thermal barrier to assess its thermal resistance in a rocket environment. The current tests combined with other planned rocket motor and joint simulation tests will enable Thiokol and NASA to decide on the optimal braid architecture for the thermal barrier. Based on the results of the current tests, the following conclusions are made:

1. The Carbon-6 (0.260-in. diam.) and Carbon-3 (0.20-in. diam.) thermal barrier resisted the 5500 °F flame of an oxyacetylene torch for over 6 min before burn through, greater than three times the Shuttle solid rocket motor burn time.

2. Carbon-3 and Carbon-6 thermal barriers were excellent insulators causing temperature drops through their diameter from 2500 to 2800 °F, depending on test parameters. Gas temperature 1/4" downstream of the thermal barrier were within the downstream Viton O-ring temperature limit of ≤600 °F.

3. The Carbon-6 thermal barrier design performed extremely well in subscale rocket “char” motor tests that subjected it to hot gas at 3200 °F for an 11-sec. rocket firing, simulating the maximum downstream joint-cavity fill-time. The thermal barrier reduced the incoming hot gas temperature by 2200 °F in an intentionally oversized gap

defect, spread the incoming jet flow, and blocked hot slag, thereby offering protection to the downstream O-rings.

4. Laboratory burn, temperature drop, flow, and compression tests and subscale rocket “char” motor tests demonstrate the thermal barrier’s feasibility for use in rocket applications and qualify it for comprehensive motor evaluation.

References

- ¹Steinetz, B.M., Adams, M.L., Bartolotta, P.A., Darolia, R., and Olsen, A., “High Temperature Braided Rope Seals for Static Sealing Applications,” NASA TM–107233, rev., July 1996.
- ²Steinetz, B.M., and Adams, M.L., “Effects of Compression, Staging, and Braid Angle on Braided Rope Seal Performance,” NASA TM–107504, July 1997.
- ³Steinetz, B.M., and Dunlap, P.H., “Feasibility Assessment of Thermal Barrier Seals for Extreme Transient Temperatures,” NASA TM–208484, July 1998.
- ⁴Thiokol report TWR-73191, “RSRM-45A Nozzle Joint No. 3 O-ring Erosion Investigation Team-Final Report,” October 28, 1996.
- ⁵Rogers, W.P., “Report of the Presidential Commission on the Space Shuttle Challenger Accident,” June 6, 1986.
- ⁶Ballis, W., ASM Handbook, Volume 6: Welding, Brazing, and Soldering, ASM International, 1993, pp. 281–290.
- ⁷Bahl, O.P. and Dhami, T.L., “Oxidation Resistance of Carbon Fibers,” High Temperatures - High Pressures, Vol. 19, pp. 211–214, 1987.
- ⁸Eckstein, B.H. and Barr, J.B., “An Accelerated Oxidation Test for Oxidation Resistant Carbon Fibers,” Materials–Processes: The Intercept Point; Proceedings of the Twentieth International SAMPE Technical Conference, Minneapolis, MN, Sept. 27–29, 1988. Covina, CA, Society for the Advancement of Materials and Process Engineering, 1988, pp. 379–391.
- ⁹Eckstein, B.H., “The Weight Loss of Carbon Fibers in Circulating Air,” 18th International SAMPE Technical Conference, October 7–9, 1986, pp. 149–160.
- ¹⁰Lide and Kehiaian, CRC Handbook of Thermophysical and Thermochemical Data, CRC Press, 1994, pp. 25–31.
- ¹¹*Parker O-ring Handbook*, Cleveland, OH, 1992.

TABLE I.—THERMAL BARRIER CONSTRUCTION MATRIX

Barrier type	Size Diameter, in.	Core				Sheath						
		Material	Denier	Fiber diameter, in. ^a	Number of yarns	Material	Denier	Fiber diameter, in. ^a	Number of layers	Number of carriers per layer	Number of yarns per bundle	Braid angle, degrees
Carbon												
Carbon-1	0.114	Grafil ^b 34-700 12K	7200	2.76×10 ⁻⁴	4	Thornel ^c T-300 1K	600	2.8×10 ⁻⁴	5	8	1	45
Carbon-2	0.125	Grafil 34-700 12K 34-700 3K	7200 1800	2.76×10 ⁻⁴	1 1	Thornel T-300 1K	600	2.8×10 ⁻⁴	10	8	1	45
Carbon-2A	0.125	Grafil 34-700 12K 34-700 3K	7200 1800	2.76×10 ⁻⁴	1 1	Thornel T-300 1K	600	2.8×10 ⁻⁴	9	8	1	45
Carbon-3	0.200	Grafil 34-700 12K	7200	2.76×10 ⁻⁴	10	Thornel T-300 1K	600	2.8×10 ⁻⁴	5	12 in 1-2 24 in 3-5	1	65 in 1 st 60 in 5 th
Carbon-4	0.194	Amoco ^d P25 2K	2900	4.4×10 ⁻⁴	21	Thornel T-300 1K	600	2.8×10 ⁻⁴	5	12 in 1-2 24 in 3-5	1	65 in 1 st 60 in 5 th
Carbon-6	0.260	Grafil 34-700 12K	7200	2.76×10 ⁻⁴	1	Thornel T-300 1K T-300 3K	600 1800	2.8×10 ⁻⁴	10	8 in 1-5 12 in 6-7 16 in 8-10	1	17 in 1 st 45 in 2-10
All-Ceramic												
NTWAC-2	0.120	NX 550 ^e	700	3.2×10 ⁻⁴	109	NX 550	700	3.2×10 ⁻⁴	2	8	1	56

^a1×10⁻³ in. = 25 μm.

^bGrafil type 34-700 carbon fibers, Grafil Inc. product. 12K-12,000 fiber ends.

^cThornel T-300 carbon fibers, Amoco Performance Products, Inc. product.

^dAmoco P25 pitch fibers, Amoco Performance Products, Inc. product.

^eNX 550 = Nextel 550 fiber, 3M product, 73% Al₂O₃, 27% SiO₂

TABLE II.—MEASURED THERMAL BARRIER POROSITY AT 20% COMPRESSION

Thermal barrier type	Number of sheath layers	Diameter, in.	Thermal barrier density, lb/cu.in.	Carbon fiber density, lb/ cu.in.	Porosity ^a
Carbon-3	5	0.200	0.041	0.064	0.37
Carbon-6	10	0.260	0.032	0.064	0.50

^aPorosity = 1 - ρ_{TB}/ρ_{CF}.

TABLE III.—TEMPERATURE DROP TEST RESULTS

(a) Carbon-3 Temperature Drop Test Results

Test number	Exposure time		T _{hot} at 15 sec, °F	T _{bulk} at 15 sec, °F	T _{hot} - T _{bulk} at 15 sec, °F	T _{hot} - T _{cold} at 15 sec, °F	Flow at 15 sec, SCFM/in.	T _{bulk} maximum, °F	Recession after test	
	Per test, sec	Accumulated, sec							in.	Percent
30	30	30	3070	210	2860	2330	0.14	310	---	---
31	30	60	3050	230	2820	2300	.14	340	---	---
32	60	120	3020	200	2820	2250	.14	500	---	---
33	60	180	2590	150	2440	1920	.14	340	0.029	13

(b) Carbon-6 Temperature Drop Test Results

Test number	Exposure time		T _{hot} at 15 sec, °F	T _{bulk} at 15 sec, °F	T _{hot} - T _{bulk} at 15 sec, °F	T _{hot} - T _{cold} at 15 sec, °F	Flow at 15 sec, SCFM/in.	T _{bulk} maximum, °F	Recession after test	
	Per test, sec	Accumulated, sec							in.	Percent
35	30	50	2730	170	2560	2050	0.24	320	---	---
36	30	80	2690	190	2500	1960	0.24	350	---	---
37	60	140	2520	280	2240	1760	0.25	480	---	---
38	60	200	2700	280	2420	1700	0.24	620	0.092	30

TABLE IV.—THERMAL BARRIER CONTACT WIDTH, PRELOAD, AND RESIDUAL INTERFERENCE FOR SEVERAL LINEAR CRUSH CONDITIONS

Thermal barrier type	Diameter, in.	Nominal percent linear crush, percent	Linear crush, in.	Number of sheath layers	Contact width, in.	Preload, psi	Residual interference, ^a in.
Carbon-3	0.2	20	0.040	5	0.063	310	0.019
		25	.050		.082	490	.027
		30	.060		.099	930	.033
Carbon-6	0.26	20	0.052	10	0.157	56	0.025
		25	.065		.192	80	.036
		30	.078		.196	97	.041

^aResidual interference is defined as the distance that the thermal barrier will spring back while maintaining a load of at least 1 lb/in. of specimen.




Figure 1.—Potential Shuttle solid rocket motor joint locations for thermal barrier.
 (a) Enlarged view of nozzle-to-case joint showing J-leg, wiper, primary, and secondary O-rings, leak-check port, and proposed thermal barrier location.
 (b) Overall nozzle cross-section (half view).




Figure 2.—Schematic of temperature drop test fixture.




Figure 3.—Schematic of flow fixture.




Figure 4.—Schematic of compression fixture.




Figure 5.—Oxyacetylene torch burn test results (n = number of tests performed).




Figure 6.—Temperature rise vs. time for simulated hot gas exposure showing upstream (hot) and downstream (cold) temperatures for Carbon-3. Left hand temperatures removed for clarity.




Figure 7.—Temperature rise vs. time for simulated hot gas exposure showing upstream (hot) and downstream (cold) temperatures for Carbon-6. Left hand temperatures removed for clarity.




Figure 8.—Temperature drop vs. time ($T_{hot}-T_{bulk}$) at flame location for Carbon-3 and Carbon-6.






Figure 9.—Hot side and cold side temperatures versus axial position at 15 seconds showing jet (0.082 in. diameter) spreading for thermal barriers (a) Carbon-3; (b) Carbon-6.



(a) Carbon-3 Temperature Drop Test Results

(b) Carbon-6 Temperature Drop Test Results

Test#	Exposure Time		T_{hot}	T_{bulk}	$T_{hot}-T_{bulk}$	Test#	Exposure Time		T_{hot}	T_{bulk}	$T_{hot}-T_{bulk}$
	Per test	Accumulated	@ 15 sec	@ 15 sec	@ 15 sec		Per test	Accumulated	@ 15 sec	@ 15 sec	@ 15 sec
	(sec)	(sec)	(°F)	(°F)	(°F)		(sec)	(sec)	(°F)	(°F)	(°F)
30	30	30	3070	210	2860	35	30	50	2730	170	2560
31	30	60	3050	230	2820	36	30	80	2690	190	2500
32	60	120	3020	200	2820	37	60	140	2520	280	2240
33	60	180	2590	150	2440	38	60	200	2700	280	2420

Figure 10.—Thermal barrier condition and key temperatures versus accumulated time. (a) Carbon-3, (b) Carbon-6.




Figure 11.—The effect of temperature, thermal barrier type, scrubbing and compression on flow, $\Delta P = 60$ psid.




Figure 12.—Subscale (70 lbm) "char" motor tests examining thermal barrier (Carbon-6) effectiveness. (a) Test configuration: Carbon-6 thermal barrier impedes hot gas flow through intentional joint defect (0.06 in. gap). (b) Temperature data: Upstream (T_{hot}) and downstream (T_{cold}) sides of thermal barrier. (Courtesy of Thiokol Corp.)




Figure 13.—Photograph of char motor thermal barrier (Carbon-6) after test. Thermal barrier effectively blocks 3200 °F gas for 11 sec. (joint fill time) and blocks hot slag. (Courtesy of Thiokol Corp.)

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (<i>Leave blank</i>)		2. REPORT DATE June 1999	3. REPORT TYPE AND DATES COVERED Technical Memorandum	
4. TITLE AND SUBTITLE Development of Thermal Barriers for Solid Rocket Motor Nozzle Joints			5. FUNDING NUMBERS WU-523-53-13-00	
6. AUTHOR(S) Bruce M. Steinetz and Patrick H. Dunlap, Jr.				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration John H. Glenn Research Center at Lewis Field Cleveland, Ohio 44135-3191			8. PERFORMING ORGANIZATION REPORT NUMBER E-11738	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546-0001			10. SPONSORING/MONITORING AGENCY REPORT NUMBER NASA TM-1999-209278 AIAA-99-2823	
11. SUPPLEMENTARY NOTES Prepared for the 35th Joint Propulsion Conference & Exhibit cosponsored by AIAA ASME, SAE, and ASEE, Los Angeles, California, June 20-24, 1999. Bruce M. Steinetz, NASA Glenn Research Center, and Patrick H. Dunlap, Jr., Modern Technologies Corporation, Middleburg Heights, Ohio. Responsible person, Bruce M. Steinetz, organization code 5950, (216) 433-3302.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Unclassified - Unlimited Subject Category: 37 This publication is available from the NASA Center for AeroSpace Information, (301) 621-0390.			12b. DISTRIBUTION CODE Distribution: Nonstandard	
13. ABSTRACT (<i>Maximum 200 words</i>) The Space Shuttle solid rocket motor case assembly joints are sealed using conventional O-ring seals. The 5500+°F combustion gases are kept a safe distance away from the seals by thick layers of insulation. Special joint-fill compounds are used to fill the joints in the insulation to prevent a direct flowpath to the seals. On a number of occasions, NASA has observed in several of the rocket nozzle assembly joints hot gas penetration through defects in the joint-fill compound. The current nozzle-to-case joint design incorporates primary, secondary and wiper (inner-most) O-rings and polysulfide joint-fill compound. In the current design, 1 out of 7 motors experience hot gas to the wiper O-ring. Though the condition does not threaten motor safety, evidence of hot gas to the wiper O-ring results in extensive reviews before resuming flight. NASA and solid rocket motor manufacturer Thiokol are working to improve the nozzle-to-case joint design by implementing a more reliable J-leg design and a thermal barrier. This paper presents burn-resistance, temperature drop, flow, and resiliency test results for several types of NASA braided carbon-fiber thermal barriers. Burn tests were performed to determine the time to burn through each of the thermal barriers when exposed to the flame of an oxy-acetylene torch (5500 °F), representative of the 5500 °F solid rocket motor combustion temperatures. Thermal barriers braided out of carbon fibers endured the flame for over 6 min, three times longer than solid rocket motor burn time. Tests were performed on two thermal barrier braid architectures, denoted Carbon-3 and Carbon-6, to measure the temperature drop across and along the barrier in a compressed state when subjected to the flame of an oxyacetylene torch. Carbon-3 and Carbon-6 thermal barriers were excellent insulators causing temperature drops through their diameter of up to a 2800 and 2560°F, respectively. Gas temperature 1/4" downstream of the thermal barrier were within the downstream Viton O-ring temperature limit of 600 °F. Carbon-6 performed extremely well in subscale rocket "char" motor tests when subjected to hot gas at 3200 °F for an 11-sec. rocket firing, simulating the maximum downstream joint cavity fill time. The thermal barrier reduced the incoming hot gas temperature by 2200 °F in an intentionally oversized gap defect, spread the incoming jet flow, and blocked hot slag, thereby offering protection to the downstream O-rings.				
14. SUBJECT TERMS Seals; Space Shuttle; Solid rocket motor; Fluid flow, Design thermal barrier; Test; Carbon; Braid			15. NUMBER OF PAGES 25	
			16. PRICE CODE A03	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT	